



Technical Data

LIP VERGE' PRIMASAFE 7014 VGL7014

Properties	Standards	Units	Target	Min	Max
Basis Weight	ISO 536	g/m ²	26.50	25.50	27.50
Thickness	ISO 534	µm	41.00	37.00	45.00
Coresta Porosity	ISO 2965	ml/mn/cm ²	70.00	66.00	74.00
Tensile strength MD	ISO 1924/1	daN/30mm	3.20	2.80	
Elongation MD	ISO 1924/1	%	1.40	1.20	
CaCO ₃ content	MO LA 42	%	26.00	24.00	
% Citrate anhydrous K	Conductivity	%	1.30	1.15	1.45
ISO Opacity	ISO 2471	%	73.00	70.00	
ISO Brightness	ISO 2470	%	89.00	88.00	
FSC bands width		mm	7.00		
FSC bands Diffusivity	SODIM D-95	cm/s	0.14		
Woodpulp	-	%	100.00		

The information and recommendation contained herein represent the best information available to BTS at the time of preparation. This information can be change at anytime without notice.